

Laboratory test

ON WOOD TABLE TOPS

ASTM-D-1308-57 METHOD

The following chart illustrates the quality of our matte and glossy finishes which withstood the use of all standard domestic products.

ELEMENT	24 HOUR EXPOSURE
Bleach	No effect
China ink	No effect
Coca-cola	No effect
Coffee	No effect
Diluted ammonia	No effect
Ethyl alcohol (100%)	Slight softening
Grape juice	No effect
Iodine	No effect
Ketchup	No effect
Lipstick	No effect
Mustard	No effect
Naptha	No effect
Olive oil	No effect
Tea	No effect
Vinegar	No effect
Water	No effect
Whiskey	No effect